## Habia Cable

## HFR 150 / Si

Intended for general use

	Elec	trical			
Properties	Method	Conditions	Value 3.0		
Dielectric constant	DIN 53483 / VDE 0303 p4	-			
Dielectric strength	-	-	-		
Dissipation factor	DIN 53483 / VDE 0303 p4	50 Hz	0.005		
Volume resistivity	-	-	10^11 Ω x cm		
	Phy	sical			
Properties	Method	Conditions	Value		
Density	DIN 53479	-	1.2 g/cm <sup>3</sup>		
Elongation at break	IEC 60811-501	50 mm/min	250 %		
Hardness	DIN 53505	-	> 70 A		
Radiation resistance	Internal	-	10^5 Gy		
Tensile strength	IEC 60811-501	50 mm/min	7 MPa		
Water absorption	-	-	-		
	The	rmal			
Properties	Method	Conditions	Value		
Combustion corrosivity	-	-	-		
Continuous temperature rating	IEC 60216	20,000 hrs	+ 180 °C		
Flammability	-	-	-		
Flame propagation	IEC 60332-1-2	Dependent on cable design	Pass		
Oxygen index	-	-	-		
Smoke density	-	-	-		
Smoke index	-	-	-		
Temperature index	-	-	-		
Toxicity index	-	-	-		

## **Properties**

HFR 150 is a very flexible rubber material ideal for use in higher temperatures. Although there is a trace of chlorine among the additives used, it is low enough to enable the material to be rated as halogen free.

There are many different grades of HFR 150 available with different properties including abrasion resistant, FDA and BfR XV approved types. Note: not all types can be supplied in all colours.

Important: Habia Cable has compiled the information contained herein from what it believes to be accurate and factual sources as of the date printed. Data is based on typical values and might vary depending on cable construction and processing method. Any changes in the data will be made without notification.



	Available colours (shades may vary from material to material)											
Black	Brown	Red	Orange	Yellow	Green	Blue	Viole	t Grey	White	Pink	-	
	Characteristics and key properties											
Intended	Intended <sup>USE</sup>	Intended <sup>USE</sup>						<b>Temp</b> installation	Temp low	<b>Temp</b> >20,000 hrs	<b>Temp</b> peak	

DISCLAIMER: This document and its content remain the property of Habia Cable. It may not be used, copied or provided to any other party than the intended recipient, without prior written permission from Habia Cable. The product shown is intended for professional use and is subject to the user's own evaluation for any particular purpose. Information provided indicates nominal, indicative values and cannot be considered a binding representation or warranty for products and their use. Information is considered valid at the time of publication and is subject to change without notice.